材料及工程實驗室-高雄

試 驗 報 告

報告號碼：KV-09-08758X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委 託 單 位：南亞塑膠工業股份有限公司
樣 品 名 稱：南亞舒活地板(NAN YA FLOORING TILE)
樣 品 型 號：企口
送 驗 人 員：南亞塑膠工業股份有限公司(郭敏泉)
收 件 日 期：98 年 10 月 23 日
試 驗 日 期：98 年 10 月 23 日~98 年 11 月 11 日
試 驗 方 法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試 驗 結 果：

試驗項目	試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
外觀	距離 2m 處以肉眼觀察無污垢、斑點、指紋、刮痕、異物、損傷或其它有礙使用之缺點	距離 2m 處以肉眼觀察無缺點發生

---oOo---

本報告若有提供規範值時，該規範要求值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360879

2007

SGS Taiwan Ltd. 台灣檢驗科技股份有限公司 | No.61, Kai -Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com
Member of SGS Group

材料及工程實驗室-高雄

試 驗 報 告

報告號碼：KV-09-08766X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委 託 單 位：南亞塑膠工業股份有限公司
樣 品 名 稱：南亞舒活地板(NAN YA FLOORING TILE)
樣 品 型 號：企口
送 驗 人 員：南亞塑膠工業股份有限公司(郭敏泉)
收 件 日 期：98 年 10 月 23 日
試 驗 日 期：98 年 10 月 23 日~98 年 11 月 11 日
試 驗 方 法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試 驗 結 果：

試驗項目	試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
表面耐磨性(回轉數)	450	1000 以上

-----oOo-----

本報告若有提供規範值時，該規範要求值僅供參考，合格之判定以委託單位實際要求為準。

劉中之
報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360880

2007

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司
No.61, Kai –Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com

Member of SGS Group

材料及工程實驗室-高雄

試驗報告

報告號碼：KV-09-08767X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委託單位：南亞塑膠工業股份有限公司
樣品名稱：南亞舒活地板(NAN YA FLOORING TILE)
樣品型號：企口
送驗人員：南亞塑膠工業股份有限公司(郭敏泉)
收件日期：98 年 10 月 23 日
試驗日期：98 年 10 月 23 日~98 年 11 月 11 日
試驗方法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試驗結果：

試驗項目		試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
耐沸水性	a.質量增加率(%)	6.76	10 以下
	b.厚度膨脹率(%)	11.02	10 以下
	c.外觀	以肉眼觀察外觀有膨脹、起泡及分層剝離現象	以肉眼觀察,除失去光澤外無其它缺點發生

----oOo----

本報告若有提供規範值時,該規範要求值僅供參考,合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360881

2007

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司
No.61, Kai –Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com

Member of SGS Group

材料及工程實驗室-高雄

試 驗 報 告

報告號碼：KV-09-08768X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委 託 單 位：南亞塑膠工業股份有限公司
樣 品 名 稱：南亞舒活地板(NAN YA FLOORING TILE)
樣 品 型 號：企口
送 驗 人 員：南亞塑膠工業股份有限公司(郭敏泉)
收 件 日 期：98 年 10 月 23 日
試 驗 日 期：98 年 10 月 23 日~98 年 11 月 11 日
試 驗 方 法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試 驗 結 果：

試驗項目	試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
耐乾熱性	以肉眼檢查試片外觀無起泡、龜裂、褪色現象,但有微失光澤之缺點	以肉眼觀察,除失去光澤外無其它缺點發生

----- o O o -----

本報告若有提供規範值時,該規範要求值僅供參考,合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360882

2007

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司
No.61, Kai -Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan / 高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com

材料及工程實驗室-高雄

試 驗 報 告

報告號碼：KV-09-08769X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委 託 單 位：南亞塑膠工業股份有限公司
樣 品 名 稱：南亞舒活地板(NAN YA FLOORING TILE)
樣 品 型 號：企口
送 驗 人 員：南亞塑膠工業股份有限公司(郭敏泉)
收 件 日 期：98 年 10 月 23 日
試 驗 日 期：98 年 10 月 23 日~98 年 11 月 11 日
試 驗 方 法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試 驗 結 果：

試驗項目			試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
尺度安定性	a.尺度變化率	縱向(%)	0.36	0.45 以下
		橫向(%)	1.45	0.90 以下
	b. 外觀		以肉眼觀察,除失去光澤外無其它缺點發生	以肉眼觀察,除失去光澤外無其它缺點發生

----- o O o -----

本報告若有提供規範值時,該規範要求值僅供參考,合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360883

2007

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司
No.61, Kai -Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com

材料及工程實驗室-高雄

試 驗 報 告

報告號碼：KV-09-08770X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委 託 單 位：南亞塑膠工業股份有限公司
樣 品 名 稱：南亞舒活地板(NAN YA FLOORING TILE)
樣 品 型 號：企口
送 驗 人 員：南亞塑膠工業股份有限公司(郭敏泉)
收 件 日 期：98 年 10 月 23 日
試 驗 日 期：98 年 10 月 23 日~98 年 11 月 11 日
試 驗 方 法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試 驗 結 果：

試驗項目	試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
耐衝擊性	以肉眼觀察外觀無破裂、凹陷等缺點	以肉眼觀察,無龜裂、膨脹、剝離等缺點

---oOo---

本報告若有提供規範值時,該規範要求值僅供參考,合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360884

2007

SGS Taiwan Ltd. 台灣檢驗科技股份有限公司 | No.61, Kai –Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com

Member of SGS Group

材料及工程實驗室-高雄

試 驗 報 告

報告號碼：KV-09-08772X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委 託 單 位：南亞塑膠工業股份有限公司
樣 品 名 稱：南亞舒活地板(NAN YA FLOORING TILE)
樣 品 型 號：企口
送 驗 人 員：南亞塑膠工業股份有限公司(郭敏泉)
收 件 日 期：98 年 10 月 23 日
試 驗 日 期：98 年 10 月 23 日~98 年 11 月 11 日
試 驗 方 法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試 驗 結 果：

試驗項目	試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
耐污染性		最後檢查時,無起泡及褪色等缺點發生
1.茶	無影響	
2.咖啡	無影響	
3.牛奶	無影響	
4.食用醋	無影響	
5.檸檬酸 10%	無影響	
6.乙醇 95%	無影響	
7.丙酮	無影響	
8.三氯乙烷	無影響	

-----oOo-----

本報告若有提供規範值時,該規範要求值僅供參考,合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360886

2007

SGS Taiwan Ltd. 台灣檢驗科技股份有限公司
No.61, Kai -Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com

材料及工程實驗室-高雄

試 驗 報 告

報告號碼：KV-09-08771X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委 託 單 位：南亞塑膠工業股份有限公司
樣 品 名 稱：南亞舒活地板(NAN YA FLOORING TILE)
樣 品 型 號：企口
送 驗 人 員：南亞塑膠工業股份有限公司(郭敏泉)
收 件 日 期：98 年 10 月 23 日
試 驗 日 期：98 年 10 月 23 日~98 年 11 月 11 日
試 驗 方 法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試 驗 結 果：

試驗項目	試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
耐龜裂性(等級)	0 (無任何改變，且無細髮狀之龜裂)	1 以上 (以六倍之放大鏡可看出不規則之細髮狀龜裂)

----- o O o -----

本報告若有提供規範值時，該規範要求值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360885

2007

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司
No.61, Kai -Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan / 高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com

材料及工程實驗室-高雄

試 驗 報 告

報告號碼：KV-09-08773X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委 託 單 位：南亞塑膠工業股份有限公司
樣 品 名 稱：南亞舒活地板(NAN YA FLOORING TILE)
樣 品 型 號：企口
送 驗 人 員：南亞塑膠工業股份有限公司(郭敏泉)
收 件 日 期：98 年 10 月 23 日
試 驗 日 期：98 年 10 月 23 日~98 年 11 月 11 日
試 驗 方 法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試 驗 結 果：

試驗項目		試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
耐光性	a.外觀	以肉眼觀察,無龜裂、膨脹、剝離等缺點	以肉眼觀察,無龜裂、膨脹、剝離等缺點
	b.Lab 色差	3.91	3 以下

-----oOo-----

本報告若有提供規範值時,該規範要求值僅供參考,合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360887

2007

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司
No.61, Kai –Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com
Member of SGS Group

材料及工程實驗室-高雄

試驗報告

報告號碼：KV-09-08774X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委託單位：南亞塑膠工業股份有限公司
樣品名稱：南亞舒活地板(NAN YA FLOORING TILE)
樣品型號：企口
送驗人員：南亞塑膠工業股份有限公司(郭敏泉)
收件日期：98 年 10 月 23 日
試驗日期：98 年 10 月 23 日~98 年 11 月 11 日
試驗方法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試驗結果：

試驗項目	試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
耐菸灼性 香菸直接燒灼法	以肉眼觀察,試片表面有不可清除之灼痕、龜裂及起泡等缺點	以肉眼觀察,除有輕微失去光澤及微棕色外無其它缺點發生

----- o O o -----

本報告若有提供規範值時,該規範要求值僅供參考,合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360888

2007

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司
No.61, Kai –Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com

材料及工程實驗室-高雄

試驗報告

報告號碼：KV-09-08775X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委託單位：南亞塑膠工業股份有限公司
樣品名稱：南亞舒活地板(NAN YA FLOORING TILE)
樣品型號：企口
送驗人員：南亞塑膠工業股份有限公司(郭敏泉)
收件日期：98 年 10 月 23 日
試驗日期：98 年 10 月 23 日~98 年 11 月 11 日
試驗方法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試驗結果：

試驗項目		試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
抗彎強度(kgf/mm²)	裝飾面	2.43	12.7 以上
	背面	2.32	8.5 以上

----- o O o -----

本報告若有提供規範值時，該規範要求值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360889

2007

SGS Taiwan Ltd. 台灣檢驗科技股份有限公司 | No.61, Kai -Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com
Member of SGS Group

材料及工程實驗室-高雄

試 驗 報 告

報告號碼：KV-09-08776X
頁　　數：1　OF　1
日　　期：98 年 11 月 12 日

委託單位：南亞塑膠工業股份有限公司
樣品名稱：南亞舒活地板(NAN YA FLOORING TILE)
樣品型號：企口
送驗人員：南亞塑膠工業股份有限公司(郭敏泉)
收件日期：98 年 10 月 23 日
試驗日期：98 年 10 月 23 日~98 年 11 月 11 日
試驗方法：CNS 11367(1985)熱固性樹脂裝飾板檢驗法
備　　註：以上資料由送驗人員提供(試驗日期除外)

試驗結果：

試驗項目	試驗結果	CNS 11366(1985) 熱固性樹脂裝飾板-負重板(HD)要求值
抗拉強度(kgf/mm^2)	1.02	6.0 以上

---- o O o ----

本報告若有提供規範值時，該規範要求值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TWA1360890

2007

SGS Taiwan Ltd.
台灣檢驗科技股份有限公司
No.61, Kai –Fa Road, Nanzih Export Processing Zone, Kaohsiung, Taiwan /高雄市楠梓加工出口區開發路61號
t (886-7) 301-2121　f (886-7) 301-1165　www.tw.sgs.com

Member of SGS Group